# **Technical Datasheet**



# DOMOSIL CONSTRUCTION

# Elastomeric adhesive and sealant

## **Description**

DOMOSIL CONSTRUCTION is a one-component, elastomeric adhesive and sealant providing:

- Resistance to temperature fluctuations from -50°C to +120°C.
- Excellent bonding to any kind of building material.
- · High elasticity.
- · Great durability to aging and weather.

## Fields of application

DOMOSIL CONSTRUCTION is well-suited for sealing vertical and horizontal joints 3-40mm wide in various materials such as glass, aluminium, wood, etc., in indoor or outdoor areas. Suitable for use in swimming pools.

## **Technical data**

Colors: white, grey

Application temperature: from +5°C to +40°C Skin formation: after 15-30 min

Maturation speed: 2-3 mm/day

Joint movement

capability:  $\pm$  25%

Elastic recovery: approx. 95% SHORE A hardness: approx. 20

# **Directions for use**

#### 1. Substrate

Substrate must be free of dust, loose particles, grease, etc. It is recommended that the joint be cleaned using a paintbrush or a wire brush and then air-blasted.

To avoid undesirable soiling at joint edges, a selfadhesive paper tape is applied alongside the edges and then is removed immediately after sealing the joint (before skin formation).

#### 2. Application

Insert cartridge in the special gun and cut nozzle in a slant way so that as it does not fit into the joint but just touches and slides along the edges. DOMOSIL CONSTRUCTION is applied by driving the cartridge alongside the joint axis at a 45° angle. While still fresh, the sealant is leveled using a

# Cleaning of tools:

trowel.

Tools must be cleaned thoroughly with common solvents while material is still fresh. If material is hardened, tools can be mechanically cleaned.

# Consumption

- Joint 10mm x 10mm:1 cartridge / 2.8m of joint length.
- Joint 5mm x 5mm:
  1 cartridge / 11.2m of joint length.

## Packaging

- Cartridges of 280ml.Sausages of 600ml.
  - sages of coorni.

# Shelf life - Storage

12 months, in dry and frost-free conditions.

## Remark

DOMOSIL CONSTRUCTION should not be applied to materials where bleeding of grease may occur.

# ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS MAIN OFFICES - FACTORY:

17<sup>th</sup> km Thessaloniki - Ag. Athanasios Road, P.O. BOX 1043, 570 03 Ag. Athanasios, Greece, Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.eu e-mail: support@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical data sheet automatically cancels any previous one concerning the same product. | 07.7.20

