



**RUST-OLEUM INDUSTRIAL BRANDS
NEVERWET® AEROSOL**

DESCRIPTION AND USES

Rust-Oleum® Industrial Brands NeverWet® Aerosol is a two-step aerosol coating system that creates a moisture repelling barrier on a variety of substrates. It is suitable for use on metal, wood, aluminum, galvanized metal, PVC, concrete, masonry, asphalt, vinyl siding, fiberglass, canvas, most plastics and more. NeverWet dries to a flat haze finish and may slightly alter the color and sheen of the substrate. To ensure the final appearance is acceptable, a test patch is suggested in an inconspicuous area before applying to entire project.

This product complies with USDA FSIS regulatory sanitation performance standards for meat and poultry establishments.

PRODUCTS

SKU	Description
275182	NeverWet Base Coat
275183	NeverWet Top Coat
275185	NeverWet Kit
275918	NeverWet Kit (Canada only)

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile.

APPLICATION

Use in a well ventilated area when the temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 85% to ensure proper drying. Avoid application in very windy and dusty conditions. Protect surrounding surfaces from overspray. Overspray can carry a significant distance.

PRODUCT APPLICATION (cont.)

BASE COAT APPLICATION - Shake the can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle **DO NOT STRIKE CAN**. Contact Rust-Oleum. A test pattern on cardboard is recommended to obtain a feel for the spray pattern. Hold can upright 6-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Continue to shake the can between passes. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more base coats a few minutes apart. Allow to dry for at least 30 minutes before applying the topcoat. **DO NOT USE NEAR OPEN FLAME.**

TOP COAT APPLICATION - Shake the can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle **DO NOT STRIKE CAN**. Contact Rust-Oleum. A test pattern on cardboard is recommended to obtain a feel for the spray pattern. Hold can upright 6-12" from surface and spray in one steady pass. Avoid soaking the surface. Stop and wait for each pass to dry for 1-2 minutes. Three or four coats will give optimum results. Do not apply any other topcoat other than NeverWet as it will lose its moisture repellent properties.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Wait at least 30 minutes before exposing to water. Optimal performance is achieved after curing for 12 hours.

If water repellency is lost, lightly sand to remove any remaining Top Coat. Reapply Base Coat and Top Coat according to directions.

Clean valve immediately after use by turning can upside down and depressing spray button for 3-5 seconds (some material will be sprayed out, so be careful to not inadvertently spray yourself or other objects). If clogged, remove tip and clean in thinner. Do not insert any object into can valve opening. Properly discard empty container. Do not burn or place in trash compactor. Empty container can be recycled

REMOVAL

NeverWet can be removed from a surface by lightly sanding and wipe with xylene or mineral spirits.



TECHNICAL DATA

NEVERWET AEROSOL

PHYSICAL PROPERTIES

	BASE COAT	TOP COAT	
Resin Type	Hydrocarbon	NA	
Pigment Type	NA	NA	
MIR	1.50 Max	NA	
Fill Weight	14 ounces	14 ounces	
Solvents	Naphtha and Ester Solvents	Acetone	
Practical Coverage at Recommended DFT (assumes 15% material loss)	15-25 sq.ft./can	15-25 sq.ft./can	
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	15 minutes	30 minutes
	Handle	4 hours	NA
	Recoat	15 minutes (with itself)	1 minute (with itself)
Dry Heat Resistance	230°F (110°C)	230°F (110°C)	
Shelf Life	6 years	6 years	
Flash Point	-156°F (-104°C)	-156°F (-104°C)	
Safety Information	For additional information, see SDS		

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.